



TECHNICAL DATA

Typical Properties and Application Procedures

PRODUCT DESCRIPTION:

EZ-Dry is a quick drying oil modified urethane sealer which can be used with either water based or oil based finishes. **EZ-Dry** penetrates the bare wood, eliminates grain raise, flows well, self levels and sands easily. **EZ-Dry** is for use on residential, commercial or gym floors.

RECOMMENDED USES:

EZ-Dry is for use as the sealing coat of on residential, commercial or sports floors.

TYPICAL PROPERTIES:

Color: Light Amber

Solids Content: 35-37%

Chemical Resistance: Good

VOC: <550 grams/liter

Flash Point: 102 degrees F

Dry Time: 3-4 hours

Clean Up: Mineral Spirits

RECOMMENDED APPLICATORS:

Weighted T-Bar (woven refill), lamb's wool applicator.

COVERAGE:

450-500 square feet per gallon.

RECOMMENDED COATS:

For newly sanded wood floors use 1 coat followed by 2-3 coats water based finishes: StreetShoe® or Hydroline® Plus, Emulsion™, or oil based finishes: Basic OMU or Commercial Poly.

PACKAGING:

5 US gallon metal pail

4- 1 US gallon metal containers

APPLYING TO NEWLY INSTALLED OR SANDED FLOORS:

SURFACE PREPARATION:

Note: Always maintain adequate ventilation during all phases of the coating process.

1. Sand and prepare the floor using current, recommended NWFA/NOFMA guidelines.
2. Make the final cut with 100-120 grit sandpaper and screen with a 100-120 grit screen.

3. Vacuum. Tack the surface with a clean, lint-free cloth either dry or slightly dampened with pure mineral spirits to remove all remaining sanding residue. All surfaces must be free of contaminants, such as dirt, grease, wax and excessive moisture content.

4. Allow floor to dry 30-60 minutes with good ventilation.

SEALER APPLICATION:

Note: Always maintain adequate ventilation during all phases of the coating process.

1. Using a lamb's wool or synthetic applicator apply in the direction of the grain at a spread rate of 450-500 Sq.Ft. per gallon. Do not puddle product.
2. Allow to dry 3-4 hours. Cooler temperatures and higher humidity will extend dry times.
3. Abrade using a maroon pad with 180 grit sanding strips.
4. Vacuum. Tack the floor with a Basic Coatings microfiber mop either dry or slightly dampened with pure mineral spirits to remove all remaining sanding residue.

DRY TIME:

(75° F @ 50% RH) Dry to touch: 1-2 hrs; ready to sand 3-4 hrs. Dry times will vary under adverse atmospheric and job conditions. Adequate ventilation is imperative during the curing process. Do not apply when temperature is above 95°, below 65°, or when humidity is above 80%. Do not apply when temperatures are over 95F, below 55°F or when relative humidity is higher than 80%.

CLEAN UP:

Clean equipment with mineral spirits and dispose of used solvent according to local regulations.